



Z-XOTKtsd 12 - 192 Optical Fibre

Spec. No. 2557/1/6/3 MB

24.06.2020, page 1/2



Type: outdoor, fully dielectric



Cable construction:

1. Central element, non-metallic
2. Optical fibres
3. Loose tube
4. Filler
5. Waterblocking yarn
6. Outer sheath
7. Ripcord

CONSTRUCTION				
Element	Type	Material	Dimensions	
Fibres	ITU-T G.652D , ITU-T G.657A or according to the attached specifications			
Identification of fibres	Comply to IEC EN 60304 : Red; Green; Blue; White; Violet; Orange; Grey; Yellow; Brown; Pink; Black; Turquoise fibres above 12 in tube: Red; Green; Blue; White; Violet; Orange; Grey; Yellow; Brown; Pink; Natural; Turquoise with black ring			
Identification of tubes/elements	for each of the layers: First tube - Red, second tube - Green, other tube - natural, filler (when needed) - black			
Central support member	straight rod	Fibre Reinforced Plastic	ϕ 1.8 mm for 12, 24, 48, 72 fibres ϕ 2.3 mm for 96 and 144 fibres ϕ 3.0 mm for 192 fibres	
Secondary coating	loose tube - thermoplastic material 12 or 24 fibres	PBT	ϕ 1.8 mm for 12, 24, 48, 72 fibres 250µm ϕ 2.2 mm for 96 and 144 fibres 250µm ϕ 1.8 mm for 192 fibres 200µm	
Filling of the tube	gel	tixotropic gel		
Interstitial waterblocking	dry sealed	swelling yarn		
Outer sheath	black	HDPE	Thickness for 12, 24, 48, 72 fibres: minimum spot average	0.40 mm 0.55 mm
			Thickness for 96 and 144 fibres: minimum spot average	0.45 mm 0.60 mm
			Thickness for 192 fibres: minimum spot average	0.55 mm 0.70 mm
Attenuation @1310 nm	≤ 0.36 dB/km			
Attenuation @1550 nm	≤ 0.23 dB/km			
Marking/Printing:	TF Kable 1 cavo ottico Z-XOTKtsd 24 J (2x12) INF-ING-ST-007-18 4.0 year of production (or according to the agreement). Length marking every meter			
Standard delivery lengths	4200 ± 100 m on wooden drums			

*) Max attenuation for SMF in cable - other parameters of the fibre according to the attached specifications

TELE-FONIKA Kable S.A.

www.tfkable.com

Z-XOTKtsd 12 - 192 Optical Fibre

Spec. No. 2557/1/6/3 MB

24.06.2020, page 2/2



PARAMETERS

No. of fibres in a cable	Outer diameter of tube [mm]	No. of elements in a cable (tubes/filers)	Cable dimensions		Mechanical properties			
			Outer diameter [mm]	Cable weight [kg/km]	Max. tensile load [N]		Min. bending radius [mm]	
					Dynamic (during installation)	Static (during the operation)	Dynamic (during installation)	Static (during the operation)
12 (1x12 250µm)	1.8	1T + 5F	6.5	35	1000	500	15 x outer diameter	20 x outer diameter
24 (2x12 250µm)	1.8	2T + 4F	6.5	35	1000	500	15 x outer diameter	20 x outer diameter
48 (4x12 250µm)	1.8	4T + 2F	6.5	35	1000	500	15 x outer diameter	20 x outer diameter
72 (6x12 250µm)	1.8	6T	6.5	35	1000	500	15 x outer diameter	20 x outer diameter
96 (4x24 250µm)	2.2	4T + 2F	8.0	52	1500	750	15 x outer diameter	20 x outer diameter
144 (6x24 250µm)	2.2	6T	8.0	52	1500	750	15 x outer diameter	20 x outer diameter
192 (8x24 200µm)	1.8	8T	8.0	58	1500	750	15 x outer diameter	20 x outer diameter

ADDITIONAL MECHANICAL PROPERTIES

Test	Standard	Value	Acceptance criteria
Crush	IEC 60794-1-2-E3	1000 N; t = 15 min	$\Delta\alpha \leq 0.05$ dB, no damage
Impact	IEC 60794-1-2-E4	3 Nm, 3 impacts	$\Delta\alpha \leq 0.05$ dB after the test
Repeated bending	IEC 60794-1-2-E6	R=20xD; F=100 N 100 cycles, 90 °, 15 cycles/min	$\Delta\alpha \leq 0.1$ dB, no damage
Torsion	IEC 60794-1-2-E7	100 N, 5 cycles, 360	$\Delta\alpha \leq 0.05$ dB, no damage

ENVIRONMENTAL SPECIFICATIONS

Water penetration	IEC 60794-1-2-F5B	sample 1 m, water head 1 m, 24 hours
Temperature range		- transport/storage -40/+70 °C - installation -15/+60 °C - operation -30/+70 °C

FEATURES

- fully dielectric
- resistant to electromagnetic interferences
- secured from longitudinal water penetration
- resistant to abrasion, UV and stress corrosion

APPLICATIONS

Cable is designated for a long distance transmission of digital and analogue signals within the whole optical bandwidth used in wide and local telecom networks of any spatial configuration. Suitable for use in primary and secondary cable ducts or in the proximity to HV lines.

TELE-FONIKA Kable S.A.

www.tfkable.com

Z-XOTKtsd 12 - 192 Optical Fibre

Spec. No. 2557/1/6/3 MB

24.06.2020, page 3/2



All the information contained in this document - including tables and diagrams - is given in good faith and believed to be correct at the time of publication. The information does not constitute a warranty nor representation for which TELE-FONIKA Kable assumes legal responsibility. TELE-FONIKA Kable reserves rights to introduce changes to the document at any time.



Single Mode Fiber

ITU-T G.652 (Tables A, B, C, D) and ITU-T G.657.A1

IEC Specifications 60793-2-50



Type: Low Water Peak, Single Mode



CONSTRUCTION

Characteristic	Low water peak single mode optical fiber, which enables customers to construct high performance wired networks for voice, video, and/or data transmission. The fiber made of germanium doped silica core and a silica cladding is in compliance with ITU-T G.657.A1 and ITU-T G.652A, B, C and D. A dual layer acrylate is coated over the cladding to provide high product reliability and allows easy splicing throughout the cable life. Its low water peak characteristics and excellent stability performance against hydrogen provide broad-range operational bandwidth while maintaining full compatibility with conventional SMF with higher proof testing, the fiber gives much tolerance in cabling and installation.
Type of primary coating	dual layer UV cured acrylate
Core material composition	germanium doped silica, no boron, no phosphorous
The optical fibres inside the cable do not contain splices.	

DIMENSIONS

mode field diameter @ 1310 nm	$9.2 \pm 0.4 \mu\text{m}$
mode field diameter @ 1550 nm	$10.4 \pm 0.5 \mu\text{m}$
Core/Clad concentricity error	$\leq 0.5 \mu\text{m}$
cladding diameter	$125 \pm 0.7 \mu\text{m}$
cladding non-circularity	$\leq 0.5 \%$
coating diameter (Colored)	$250 \pm 15 \mu\text{m}$
coating/cladding eccentricity	$\leq 12 \mu\text{m}$

OPTICAL PERFORMANCE

Attenuation	Typical Values	Max. Values
- @ 1310 nm	0.33-0.35 dB/km	0.40 dB/km
- @ 1550 nm	0.19-0.22 dB/km	0.25 dB/km
- @ 1625 nm	0.20-0.24 dB/km	0.40 dB/km
- @ 1383 nm	0.31-0.35 dB/km	0.40 dB/km
Chromatic dispersion @ 1550 nm	$\leq 18 \text{ ps/nm/km}$	
Cut-off wavelength (λ_{cc})	$\leq 1260 \text{ nm}$	
Zero dispersion wavelength (λ_0)	$1300 < \lambda_0 < 1324 \text{ nm}$	
Polarization mode dispersion max. individual fiber	$\leq 0.1 \text{ ps/\sqrt{km}}$	
Polarization mode dispersion link value	$\leq 0.04 \text{ ps/\sqrt{km}}$	

All the information contained in this document - including tables and diagrams - is given in good faith and believed to be correct at the time of publication. The information does not constitute a warranty nor representation for which TELE-FONIKA Kable assumes legal responsibility. TELE-FONIKA Kable reserves rights to introduce changes to the document at any time.

TELE-FONIKA Kable S.A.

www.tfkable.com

Single Mode Fiber

ITU-T G652(Tables A,B,C,D) and ITU-T G.657.A1

IEC Specifications 60793-2-50



PERFORMANCE CHARACTERISTICS

Effective group index of refraction	1.466	@1310 nm/1383 nm
	1.467	@1550 nm
	1.470	@1625 nm

MECHANICAL PROPERTIES

proof test entire length	1.2 %
strippability; stripping force	1.3 – 8.9 N

BENDING INDUCED ATTENUATION

Mandrel Radius	Number of Turns	Wavelength	Attenuation
10 mm	1	1550 nm	≤ 0.75 dB
10 mm	1	1625 nm	≤ 1.5 dB
15 mm	10	1550 nm	≤ 0.25 dB
15 mm	10	1625 nm	≤ 1.0 dB
16 mm	1	1550 nm	≤ 0.05 dB
25 mm	100	1310/1550 nm	≤ 0.05 dB
30 mm	100	1625 nm	≤ 0.05 dB

ENVIRONMENTAL SPECIFICATIONS

Test	Test Condition	Induced attenuation @1310, 1550 & 1625 nm
Temperature humidity cycling	-10 to + 85°C up to 98%RH	≤0.05 dB/km
Temperature dependent	-60 to + 85°C	≤0.05 dB/km

Single Mode Fiber

ITU-T G.657.A1

IEC Specifications 60793-2-50 Type B1.3



Type: Low Water Peak, Single Mode, Reduced diameter



CONSTRUCTION

Characteristic	Low water peak single mode optical fiber in 200µm coating diameter for a reduced cable diameter design, which enables customers to construct high performance wired networks for voice , video, and/or data transmission. The fiber made of germanium doped silica core and a silica cladding is in compliance with ITU-T G.657A and ITU-T G.652A,B,C and D. A dual layer acrylate is coated over the cladding to provide high product reliability and allows easy splicing throughout the cable life. The fiber supports access networks including last one -mile application such like FTTH due to its excellent bending performance while maintaining compatibility with conventional SMF.
Type of primary coating	dual layer UV cured acrylate
Core material composition	germanium doped silica, no boron, no phosphorous
The optical fibres inside the cable do not contain splices.	

DIMENSIONS

mode field diameter @ 1310 nm	$8,6 \pm 0,4 \mu\text{m}$
Core/cladding concentricity error	$\leq 0,5 \mu\text{m}$
cladding diameter	$125 \pm 0,7 \mu\text{m}$
cladding non-circularity	$\leq 0,5 \%$
coating diameter (uncoloured fibre)	$205 \pm 7 \mu\text{m}$
coating/cladding eccentricity	$\leq 12 \mu\text{m}$

OPTICAL PERFORMANCE

Attenuation	Typical Values (99% fibres in cable)	Max. Values
- @ 1310 nm	0,33-0,35 dB/km	0,40 dB/km
- @ 1550 nm	0,19-0,22 dB/km	0,25 dB/km
- @ 1625 nm	0,20-0,24 dB/km	0,30 dB/km
- @ 1383 nm	0,30-0,35 dB/km	0,40 dB/km
Chromatic dispersion		
- @ 1550 nm	$\leq 18 \text{ ps}/(\text{nm} \cdot \text{km})$	
- @ 1625nm	$\leq 22 \text{ ps}/(\text{nm} \cdot \text{km})$	
Polarization mode dispersion	$\leq 0,2 \text{ ps}/\text{km}^2$	
Fiber PMD link design value	$\leq 0,08 \text{ ps}/\text{km}^2$	
Cut-off wavelength (λ_{cc})	$\leq 1260 \text{ nm}$	
Zero dispersion wavelength (λ_0)	$1300 < \lambda_0 < 1324 \text{ nm}$	

All the information contained in this document - including tables and diagrams - is given in good faith and believed to be correct at the time of publication. The information does not constitute a warranty nor representation for which TELE-FONIKA Kable assumes legal responsibility. TELE-FONIKA Kable reserves rights to introduce changes to the document at any time.

TELE-FONIKA Kable S.A.

www.tfkable.com

Single Mode Fiber

ITU-T G.657.A1

IEC Specifications 60793-2-50 Type B1.3



MECHANICAL PROPERTIES

proof test entire length	0,86 GPa	1,2 %
strippability; stripping force		1,3 – 8,9 N

Bending induce attenuation:

MECHANICAL PROPERTIES

Mandrel radius [mm]	Number of turns	Wavelength [nm]	Attenuation dB
10	1	1550	≤ 0,75
10	1	1625	≤ 1,5
15	10	1550	≤ 0,25
15	10	1625	≤ 1,0
16	1	1550	≤ 0,05
25	100	1310/1550	≤ 0,05
30	100	1625	≤ 0,05

ENVIRONMENTAL SPECIFICATIONS

Test	Test Condition	Induced attenuation @1310, 1550 & 1625 nm
Temperature humidity cycling	-10 to + 85°C up to 98%RH	≤0,05 dB/km
Temperature dependen	-60 to + 85°C	≤0,05 dB/km

PERFORMANCE CHARACTERISTICS

Effective group index of refraction	@1310nm / 1383nm	1,466
	@1550 nm	1,467
	@1625 nm	1,470